



Geoceramic Researches S.r.l.

Via Bacchello, 9
40050 Monte San Pietro BO - Italy
Tel. 051/6761738 - fax 051/6761736
e-mail : geoceramic@iol.it
home page : <http://www.geoceramic.it>



Laboratory for Experimental and Technological Ceramics and Brick Industries

TEST REPORT

N° 237/17eng

Place and Date of Issue : Monte San Pietro, 25/10/2017

Customer : GRUPPO ROMANI S.p.A.

Address : Via A. Volta, 9-23/25
42013 CASALGRANDE RE

Type material examined : Industrial Tiles

60x60 cm STONEBOX

Standards applied :

DIN 51097 : 2006

Sampling date : 23/10/2017

Sampling by :

Client



Geoceramic R.



Storage time of samples : 3 months from the end of tests.

This document may not be reproduced in part, without the approval of the Laboratory.

The data reported in the test report refer only to the sample tested as received in the Laboratory

THE VALIDITY OF DIGITAL SIGNATURE IS VERIFIABLE THROUGH THE ANALYSIS OF THE FIELD FILE ORIGINAL SIGNATURE.

Laboratory with Quality Management System ISO 9001: 2008



Geoceramic Researches S.r.l.

Via Bacchello, 9
40050 Monte San Pietro BO - Italy
Tel. 051/6761738 - fax 051/6761736
e-mail : geoceramic@iol.it
home page : <http://www.geoceramic.it>



Laboratory for Experimental and Technological Ceramics and Brick Industries

TEST REPORT

TS N°: 237/17eng

DATE 25/10/2017

Spett.le
GRUPPO ROMANI S.p.A.
Via A. Volta, 9-23/25
42013 CASALGRANDE RE

NORM DIN 51097 : 2006

Determination of the property antislip of bathed zones on which it walks knots on foot

A person is left over and on foot withdraws knots on the covering to try whose inclination is increased of approximately 1° to the second; the rake in correspondence of which the person is not more in conditions than emergency, comes defined like sliding angle. The surface is bathed in continuous with one solution (1 g/l of bathing agent + water).

Samples arrived 23/10/2017 (sampling executed by Customer)

DESCRIPTION TILES : 60x60 cm
TYPE : STONEBOX

Test start 24/10/2017
Test finished 24/10/2017

Slide angle : 22,8°

Classification : B

LEGEND:

<u>Total of the medium values</u>	<u>Group classification</u>
<12°	0
from 12° until 17,9°	A
from 18° until 23,9°	B
over 23,9°	C

Laboratory Head
P.I. Riccardo Frabetti