

STONE PLAN WALL

SPECIFICATION WHITE BODY WALL TILES

MATERIAL

White body wall tiles.

Classificate nel GROUP BIII GL CON Ev > 10%.

This material complies with all the requirements of UNI EN 14411 ISO 13006 APP. L

Italgraniti pushes back the border of ceramic coverings: matter becomes ornamentation, creating walls of immense stylistic impact and elegant naturalness. Stone plan white-body tiles are designed to be combined in total harmony, to complete every bathroom with character and style.

COLOR	SIZES	SURFACE	THICKNESS
RIGATO BIANCO			
RIGATO GRIGIO	RECTIFIED 32x96,2 (12 ^{1/2} "x37 ^{1/8} ")	SATIN	11,5 MM
RIGATO BEIGE			

PRODUCTION PROCESS

Monoporosa tiles obtained by dry pressing a compact white body mix consisting of choice clays. The surface is glossy glazed. The colours are obtained using high-purity colorant oxides. The decoration is obtained using the innovative digital technology which provides a peerless appearance, re-creating the countless vein patterns of marble with high definition and extremely precise details. The tiles are fired in single-layer roller kilns at a temperature around 1,140°C.

Size	
Finishes	
Color	Type









STONE PLAN WALL



TECHNICAL TABLE WHITE BODY WALL TILES

CONFORMING TO STANDARDS

EN 14411 ISO 13006 ANNEX L GROUP BIII GL CON Ev > 10%

	PHYSICAL PROPERTIES	TESTING METHOD	REFERENCE STANDARD			PRODUCT VALUES
			N ≥ 15 cm			
				(%)	(mm)	
			Length and width	±0.5	±2.0	_
			Thickness	±10	±0.5	_
			Lineartity	±0.3	±1.5	
			Wedging	±0.5	±2.0	Rectified
	Sizes	EN ISO 10545-2	Warpage	±0.5	±2.0	
			Centre curvature	±0.5 -0,3	±2.0 -1,5	Conforming
			Edge curvature	±0.5 -0,3	±2.0 -1,5	comorning
			Warpage	±0.5	±2.0	_
			Surface quality	95% of tiles w	vith no visible flaws	
	Water absorption %	EN ISO 10545-3	Ev >10%			Conforming
Ţ	Modulus of rupture	EN ISO 10545-4	sp. > = 7,5 mm: min 12 N/mm ²			Conforming
	Breakage resistence	EIN 13O 10343-4	sp. > = 7,5 mm: min 600 N			Conforming
	Thermal expansion coefficient	EN ISO 10545-8	Stated value			7 MK ⁻¹
	Thermal shock resistance	EN ISO 10545-9	* Testing method available			Resistant
N	Glaze crazing resistance	EN ISO 10545-11	* Testing method available			* Resistant
	Resistance to low concentrations of acids and alkali		Stated value			Resistant
	Resistance to domestic chemicals and additives for swimming pools	EN ISO 10545-13	GB min.			Conforming
*	Stain resistance of unglazed matte porcelain	EN ISO 10545-14	Classe 3 min.			Conforming