






















GENESIS LOFT



FEATURES

CER637- TECHNICAL CHARACTERISTICS GLAZED PORCELAIN STONEWARE WITH COLOURED BODY

	PROPERTY PHYSICAL - CHEMICAL	TEST METHOD	AVERAGE VALUE
	Lenght and width	ISO 10545 - 2	$\pm 0,3\% \pm 2 \text{ mm}$
	Lenght and width	ISO 10545 - 2	$\pm 0,3\% \pm 2 \text{ mm}$
	Straightness of sides	ISO 10545 - 2	$\pm 0,3\% \text{ max } \pm 2 \text{ mm}$
	Thickness	ISO 10545 - 2	$\pm 5\% \text{ max } \pm 0,5 \text{ mm}$
	Rectangularity	ISO 10545 - 2	$\pm 0,3\% \pm 1,5 \text{ mm}$
	Surface flatness	ISO 10545 - 2	$\pm 0,5\% \pm 2 \text{ mm}$
		ASTM C 485 Warpage diagonal/edge	$\pm 0,4\%$
	Shade variations		V 2 (Shell, Lime, Avana, Moka)
	Shade variations		V 3 (Atlantic, Blackmoon, Mineral, Fossil, Zinc)

	Water absorption	ISO 10545 - 3	E < 0,1%	
	Scratch hardness (MOHS scale)	EN 101	MOHS ≥ 6	
	Moduls of rupture	ISO 10545 - 4	R ≥ 35 N/mm ²	
	Breaking strength	ISO 10545 - 4	S ≥ 1300 N	
	Resistance to surface abrasion of glazed tiles	ISO 10545 - 7	Class 4	
	Linear thermal expansion coefficient	ISO 10545 - 8	Method available	
	Thermal shock resistance	ISO 10545 - 9	Resistant	
	Frost resistance	ISO 10545 - 12	Ingelif	
	Resistance to chemical attack (except hydrofluoric acid)	ISO 10545 - 13	Class GA - GLA	
	Resistance to stains of glazed tiles	ISO 10545 - 14	Class 5	
	Skid resistance. Average coefficient of friction (R10)	B.C.R.A. REP. CEC. 6/81 (no lapp)	0,40 ≤ μ ≤ 0,74	
		DIN 51130 (no lapp)	R 10	
		DIN 51097 (no lapp)	Class B	
		DCOF Acu Test (no lapp)	μ ≥ 0,42	



Skid resistance. Average coefficient of

B.C.R.A. REP. CEC. 6/81 (no lapp)

test in update

friction (R11)

DIN 51130 (no lapp)

test in update

DIN 51097 (no lapp)

test in update

DCOF Acu Test (no lapp)

test in update

CERCOM CERAMICHE
www.cercomceramiche.it



Show-room: Via A. Volta 23/25 - 42013 Casalgrande (RE) Italy

Headquarter: Via A. Volta 9,23/25 - 42013 Casalgrande (RE) Italy

Contatti commerciali: Tel. +39-0522-998411/911 - Fax Italy +39-0522-998910 - Fax Export +39-0522-996218

Contatti amministrazione-finanza: Tel. +39-0522-998411/911 - Fax Clienti +39-0522-999515 - Fax Fornitori +39-0522-996600 -

Fax Acquisti +39-0522-998474

Sede logistica deposito 5: Via Platone 9 - 42048 Rubiera (RE) Italy - Tel. +39-0522-622622

© Gruppo Romani S.p.A. Industrie Ceramiche

Via A. Volta 9-23/25 - 42013 Casalgrande (RE) Italy - Tel. +39-0522-998411/911 - Fax +39-0522-999515/996600

C.F. e P.IVA 03028130361 - Cap. Soc. € 4.100.000,00 i.v. - REA di RE n.260001 - Iscr. Reg. Impr. di RE n.

03028130361 - Mecc. n. RE027834

www.grupporomanispa.com

[Reserved Area](#) | [Privacy Policy](#) | [Cookie Policy](#) | [GDPR Policies](#) | [Disclaimer](#) | [General conditions of sale](#) | [Laying and cleaning](#) | [Certifications](#)