

<i>Requested by:</i>	GRUPPO ROMANI INDUSTRIE CERAMICHE S.p.A. Via Platone, 9 – 42018 RUBIERA (RE)	
<i>For the sample:</i>	Glazed ceramic tiles 30 x 60 x 1,0 cm marked "Serie GENESIS RET".	
<i>On (date):</i> 07/07/16	<i>Date of receipt in laboratory (sample delivered by the client):</i> 07/07/16	
<i>Test date</i>	<i>From:</i> 21/07/16	<i>To:</i> 21/07/16

Slip resistance (D.M. 14/06/1989 – n° 236)

TEST CONDITIONS:

- Speed of travel (mm/s): 17
- Load applied to slider (g): 200


RESULTS

<i>Slider material</i>	<i>Surface condition</i>	<i>Average coefficient of friction (μ)</i>
Leather	Dry	0,46
Hard shoe-heeling rubber	Wet (water+wetting agent)	0,48

Requirements (D.M. 14/06/1989 N°236 Part. 8.2.2 and D.P.R 24/07/1996, n. 503)

Average coefficient of friction $\mu > 0,40$

Eng. Giordana Carani
Technical approval



Prof. Maria Chiara Bignozzi
Director



The results reported relate only to the samples tested. No responsibility is taken for the accuracy of the sampling unless it is done under our own supervision. The reproduction of this test report is only authorized in the form of a complete photographic facsimile. Our written approval is necessary for any partial reproduction. This test report consists of 1 pages, this cover included.