



Sizes	50x120 cm 19"x47 1/4" 8.5mm
-------	--------------------------------

		Technical features	Test method	Requisites for nominal size N			Prism
				7 cm ≤ N < 15 cm (mm)	N ≥ 15 cm (%)		Matte rectified
Regularity features		Length and width	ISO 10545-2	± 0,4 (*) Rect.	± 0,3 (*) Rect.	± 1,0 (*) Rect.	Suitable for
		Thickness		± 0,5 (**)	± 10 (**)	± 0,5 (**)	Suitable for
		Straightness of sides		± 0,4 (***) Rect.	± 0,3 (***) Rect.	± 0,8 (***) Rect.	Suitable for
		Perpendicularity		± 0,4 (***) Rect.	± 0,3 (***) Rect.	± 1,5 (***) Rect.	Suitable for
		Surface flatness		c.c. ± 0,6 Rect.	c.c. ± 0,4 Rect.	c.c. ± 1,8 Rect.	Suitable for
e.c. ± 0,6 Rect.			e.c. ± 0,4 Rect.	e.c. ± 1,8 Rect.			
Structural features		Water absorption level (in% by mass)	ISO 10545-3	Average >10%. If this value > 20%, it must be indicated. Single value > 9%			10%<EV≤20%
Bulk mechanical features		Breaking strenght	ISO 10545-4	S ≥ 600N			S ≥600 N
		Bending resistance		R ≥ 12 N/mm²			R ≥15 N/mm²
Thermo-igrometric features		Coefficient of linear thermal expansion	ISO 10545-8	Declared value			≤7MK <sup>-1</sup>
		Thermal shock resistance	ISO 10545-9	Test passed in accordance with ISO 10545-1			Resistant
		Moisture expansion (in mm/m)	ISO 10545-10	Declared value			≤0.06% (0.6mm/m)
		Crazing resistance: glazed tiles	ISO 10545-11	Test passed in accordance with ISO 10545-1			Resistant
Physical properties		Bond strenght	EN 1348	Declared value			≥1.0 N/mm² (Class C2 - EN 12004)
		Reaction to fire	-	Class A1			A1
Chemical features		Resistance to household chemicals and swimming pool salts	ISO 10545-13	Minimum B class			A
		Resistance to low concentrations of acids and alkalis		Declared class			LA
		Resistance to high concentrations of acids and alkalis		Declared class			HA
		Stain resistance of glazed tiles	ISO 10545-14	Minimum Class 3			5
		Release of dangerous substances: Cadmium (in mg/dm²) and Lead (in mg/dm²)	ISO 10545-15	Declared value			≤0.01mg/dm² Cd ≤0.1mg/dm² Pb

\* Permitted deviation, in % or mm, from the average size of each tile (2 or 4 sides) with respect to the manufacturing size (W).  
 \*\* Permitted deviation, in % or mm, from the average thickness of each tile with respect to the cited manufacturing thickness (W).  
 \*\*\* Maximum permitted straightness deviation, in % or mm, with respect to the corresponding manufacturing sizes (W).  
 \*\*\*\* Maximum permitted perpendicularity deviation, in % or mm, with respect to the corresponding manufacturing sizes (W).  
 \*\*\*\*\* Maximum permitted centre curvature deviation, in % or mm, with respect to the diagonal calculated according to manufacturing sizes (W).  
 e.c. Maximum permitted corner curvature deviation, in % or mm, with respect to the corresponding manufacturing sizes (W).  
 w. Maximum permitted bending deviation, in % or mm, with respect to the diagonal calculated according to manufacturing sizes (W).  
 (1) Determining the slip resistance of pedestrian surfaces; not applicable to sports flooring or road traffic flooring.  
 (2) The anti-slip performance is guaranteed at the time of delivering the product.  
 (3) However, tiles with a DCOF of 0.42 or greater are not necessarily suitable for all projects. The specifier shall determine tiles appropriate for specific project conditions, considering by way of example, but not in limitation, type of use, traffic, expected contaminants, expected maintenance, expected wear, and manufacturers' guidelines and recommendations."  
 (4) For further details, please refer to the outdoor design general catalogue.  
 (5) Only for products with 20 mm thickness



Sizes	120x278 cm 47 1/4"x109 1/2" ±6mm	120x120 cm 47 1/4"x47 1/4" ±9mm	120x120 cm 47 1/4"x47 1/4" ±20mm	80x80 cm 31 1/2"x31 1/2" ±20mm	60x120 cm 23 3/4"x47 1/4" ±9mm	60x60 cm 23 3/4"x23 3/4" ±9mm	30x60 cm 11 3/4"x23 3/4" ±9mm
-------	-------------------------------------	------------------------------------	-------------------------------------	-----------------------------------	-----------------------------------	----------------------------------	----------------------------------

	Technical features	Test method	Requisites for nominal size N			Prism				
			7 cm ≤ N < 15 cm	N ≥ 15 cm		Matte rectified 6mm 120x278 cm	Matte rectified 9mm	Grip rectified	Textured rectified	Silk rectified
			(mm)	(%)	(mm)					
Regularity features	 Length and width Thickness Straightness of sides Perpendicularity (Measurement only on short edges when L/l ≥ 3)	ISO 10545-2	± 0,9 (*) Non-rect. ± 0,4 (*) Rect.	± 0,6 (*) Non-rect. ± 0,3 (*) Rect.	± 2,0 (*) Non-rect. ± 1,0 (*) Rect.	Suitable for	Suitable for	Suitable for	Suitable for	Suitable for
			± 0,5 (**)	± 5 (**)	± 0,5 (**)	Suitable for	Suitable for	Suitable for	Suitable for	Suitable for
			± 0,8 (***) Non-rect. ± 0,4 (***) Rect.	± 0,5 (***) Non-rect. ± 0,3 (***) Rect.	± 1,5 (***) Non-rect. ± 0,8 (***) Rect.	Suitable for	Suitable for	Suitable for	Suitable for	Suitable for
			± 0,8 (***) Non-rect. ± 0,4 (***) Rect.	± 0,5 (***) Non-rect. ± 0,3 (***) Rect.	± 2,0 (***) Non-rect. ± 1,5 (***) Rect.	Suitable for	Suitable for	Suitable for	Suitable for	Suitable for
	 Surface flatness		c.c. ± 0,8 Non-rect. c.c. ± 0,6 Rect.	c.c. ± 0,5 Non-rect. c.c. ± 0,4 Rect.	c.c. ± 2,0 Non-rect. c.c. ± 1,8 Rect.	Suitable for	Suitable for	Suitable for	Suitable for	Suitable for
			e.c. ± 0,8 Non-rect. e.c. ± 0,6 Rect.	e.c. ± 0,5 Non-rect. e.c. ± 0,4 Rect.	e.c. ± 2,0 Non-rect. e.c. ± 1,8 Rect.					
Structural features	 Water absorption level (in% by mass)	ISO 10545-3	E ≤ 0,5% Individual Maximum 0,6%			≤0.1%	≤0.1%	≤0.1%	≤0.1%	≤0.1%
		ASTM C373-18	Requirement ANSI A137.1-2017 Water Absorption Max < 0,5%			≤0.5%	≤0.5%	≤0.5%	≤0.5%	≤0.5%
Bulk mechanical features	 Breaking strenght Bending resistance	ISO 10545-4	S ≥ 700N (for thickness < 7,5mm) S ≥ 1300N (for thickness ≥ 7,5mm)			S ≥1000 N	S ≥1500 N	S ≥1500 N	S ≥10000 N	S ≥1500 N
			R ≥ 35 N/mm²			R ≥40 N/mm²	R ≥40 N/mm²	R ≥40 N/mm²	R ≥45 N/mm²	R ≥40 N/mm²
	 Bending and breaking load resistance (4)(5)	EN 1339 Annex F	-						≥T11 120x120 90x90   ≥U4 60x120	
	 Impact resistance	ISO 10545-5	Declared value			≥0.55	≥0.55	≥0.55	≥0.55	≥0.55
Surface mechanical features	 Mohs hardness	EN 101	-			MOHS 6	MOHS 6	MOHS 8	MOHS 8	MOHS 5
	 Deep abrasion resistance of unglazed tiles	ISO 10545-6	≤ 175 mm³			≤150mm³	≤150mm³	≤150mm³	≤150mm³	≤150mm³

\* Permitted deviation, in % or mm, from the average size of each tile (2 or 4 sides) with respect to the manufacturing size (W).  
 \*\* Permitted deviation, in % or mm, from the average thickness of each tile with respect to the cited manufacturing thickness (W).  
 \*\*\* Maximum permitted straightness deviation, in % or mm, with respect to the corresponding manufacturing sizes (W).  
 \*\*\*\* Maximum permitted perpendicularity deviation, in % or mm, with respect to the corresponding manufacturing sizes (W).  
 \*\*\*\*\* Maximum permitted centre curvature deviation, in % or mm, with respect to the diagonal calculated according to manufacturing sizes (W).  
 e.c. Maximum permitted corner curvature deviation, in % or mm, with respect to the corresponding manufacturing sizes (W).  
 w. Maximum permitted bending deviation, in % or mm, with respect to the diagonal calculated according to manufacturing sizes (W).  
 (1) Determining the slip resistance of pedestrian surfaces; not applicable to sports flooring or road traffic flooring.  
 (2) The anti-slip performance is guaranteed at the time of delivering the product.  
 (3) However, tiles with a DCOF of 0.42 or greater are not necessarily suitable for all projects. The specifier shall determine tiles appropriate for specific project conditions, considering by way of example, but not in limitation, type of use, traffic, expected contaminants, expected maintenance, expected wear, and manufacturers' guidelines and recommendations."  
 (4) For further details, please refer to the outdoor design general catalogue.  
 (5) Only for products with 20 mm thickness

The technical features for the 120x278 apply to the following colors: Cotton, Cord, Suede, Fog, Cloud, Graphite / Le catteristiche tecniche per il 120x278 sono valide per i seguenti colori: Cotton, Cord, Suede, Fog, Cloud, Graphite



Sizes	120x278 cm 47 4/4"x109 1/2" 6mm	120x120 cm 47 4/4"x47 4/4" 9mm	120x120 cm 47 4/4"x47 4/4" 20mm	80x80 cm 31 1/2"x31 1/2" 20mm	60x120 cm 23 3/4"x47 4/4" 9mm	60x60 cm 23 3/4"x23 3/4" 9mm	30x60 cm 11 3/4"x23 3/4" 9mm
-------	------------------------------------	-----------------------------------	------------------------------------	----------------------------------	----------------------------------	---------------------------------	---------------------------------

	Technical features	Test method	Requisites for nominal size N			Prism				
			7 cm ≤ N < 15 cm		N ≥ 15 cm	Matte rectified 6mm 120x278 cm	Matte rectified 9mm	Grip rectified	Textured rectified	Silk rectified
			(mm)	(%)	(mm)					
Thermo-igrometric features	Coefficient of linear thermal expansion	ISO 10545-8	Declared value			≤7MK <sup>-1</sup>	≤7MK <sup>-1</sup>	≤7MK <sup>-1</sup>	≤7MK <sup>-1</sup>	≤7MK <sup>-1</sup>
	Thermal shock resistance	ISO 10545-9	Test passed in accordance with ISO 10545-1			Resistant	Resistant	Resistant	Resistant	Resistant
	Moisture expansion (in mm/m)	ISO 10545-10	Declared value			≤0.01% (0.1mm/m)	≤0.01% (0.1mm/m)	≤0.01% (0.1mm/m)	≤0.01% (0.1mm/m)	≤0.01% (0.1mm/m)
	Frost resistance	ISO 10545-12	Test passed in accordance with ISO 10545-1			Resistant	Resistant	Resistant	Resistant	Resistant
Physical properties	Bond strenght	EN 1348	Declared value			≥1.0 N/mm <sup>2</sup> (Class C2 - EN 12004)	≥1.0 N/mm <sup>2</sup> (Class C2 - EN 12004)	≥1.0 N/mm <sup>2</sup> (Class C2 - EN 12004)	≥1.0 N/mm <sup>2</sup> (Class C2 - EN 12004)	≥1.0 N/mm <sup>2</sup> (Class C2 - EN 12004)
	Reaction to fire	-	Class A1 or A1 <sub>fl</sub>			A1 - A1 <sub>fl</sub>	A1 - A1 <sub>fl</sub>	A1 - A1 <sub>fl</sub>	A1 - A1 <sub>fl</sub>	A1 - A1 <sub>fl</sub>
Chemical features	Resistance to household chemicals and swimming pool salts	ISO 10545-13	Minimum B class			A	A	A	A	A
	Resistance to low concentrations of acids and alkalis		Declared class			LA	LA	LA	LA	LA
	Resistance to high concentrations of acids and alkalis		Declared class			HA	HA	HA	HA	HA
	Stain resistance	ISO 10545-14	Declared class			5	5	5	5	5
Safety characteristics (1)(2)	Booted ramp test	DIN 51130	Declared class			R9	R10	R11	R11	N.C.
	Barefoot Ramp test	DIN 51097	Declared value			A	A+B	A+B+C	A+B+C	A
	Pendulum friction Test	BS 7976	PTV ≥ 36 classifies the surface as "low slip risk"			PTV ≥ 36 Wet on demand	≥36Dry ≥36Wet	≥36Dry ≥36Wet	≥36Dry ≥36Wet	≥ 36 Dry ≤ 24 Wet
		AS 4586	Declared Classification of the new pedestrian surface materials according to the Pendulum Test			P3 on demand	Class P3	Class P4	Class P4	
		UNE-ENV 12633 UNE 41901:2017 EX	Declared value			C2 on demand	Class C2	Class C3	Class C3	
	Coefficient of friction	B.C.R.A. Rep. CEC/81	Min. Dec. 236/89 of 14/06/89 μ >0.40 for a sliding leather element on a dry floor μ >0.40 for a sliding hard rubber element on a wet floor			>0.40Asciutto >0.40Bagnato	>0.40Asciutto >0.40Bagnato	>0.40Asciutto >0.40Bagnato	>0.40Asciutto >0.40Bagnato	>0.40Asciutto <0.40Bagnato
Dynamic coefficient of friction (DCOF)	ANSI A.137.1	ANSI A.137.1-2017 Requires a minimum value of 0.42 for level interior space expected to be walked upon when wet. (3)			> 0.42 Wet	> 0.42 Wet	> 0.42 Wet	> 0.42 Wet	> 0.42 Wet	

- \* Permitted deviation, in % or mm, from the average size of each tile (2 or 4 sides) with respect to the manufacturing size (W).
- \*\* Permitted deviation, in % or mm, from the average thickness of each tile with respect to the cited manufacturing thickness (W).
- \*\*\* Maximum permitted straightness deviation, in % or mm, with respect to the corresponding manufacturing sizes (W).
- \*\*\*\* Maximum permitted perpendicularity deviation, in % or mm, with respect to the corresponding manufacturing sizes (W).
- \*\*\*\* Maximum permitted centre curvature deviation, in % or mm, with respect to the diagonal calculated according to manufacturing sizes (W).
- e.c. Maximum permitted corner curvature deviation, in % or mm, with respect to the corresponding manufacturing sizes (W).
- w. Maximum permitted bending deviation, in % or mm, with respect to the diagonal calculated according to manufacturing sizes (W).
- (1) Determining the slip resistance of pedestrian surfaces; (not applicable to sports flooring or road traffic flooring).
- (2) The anti-slip performance is guaranteed at the time of delivering the product.
- (3) However, tiles with a DCOF of 0.42 or greater are not necessarily suitable for all projects. The specifier shall determine tiles appropriate for specific project conditions, considering by way of example, but not in limitation, type of use, traffic, expected contaminants, expected maintenance, expected wear, and manufacturers' guidelines and recommendations."
- (4) For further details, please refer to the outdoor design general catalogue.
- (5) Only for products with 20 mm thickness

The technical features for the 120x278 apply to the following colors: Cotton, Cord, Suede, Fog, Cloud, Graphite / Le caratteristiche tecniche per il 120x278 sono valide per i seguenti colori: Cotton, Cord, Suede, Fog, Cloud, Graphite