



Geoceramic Researches S.r.l.

Via Bacchello, 9
40050 Monte San Pietro BO - Italy
Tel. 051/6761738 - fax 051/6761736
e-mail : geoceramic@iol.it
home page : <http://www.geoceramic.it>



Laboratory for Experimental and Technological Ceramics and Brick Industries

TEST REPORT

TS N°: 076/18eng

DATE 04/05/2018

Spett.le
GRUPPO ROMANI S.p.A.
Via A. Volta, 9-23/25
42013 CASALGRANDE RE

NORM DIN 51130 : 2014

Determination of anti-slippery characteristic

Work's zone with high risk of slippery
Procedure of test walking – inclined platform.

The test regard work's zone with high risk of slippery; the procedure it previews a slanted plan that it comes covered from the subject participants to the test, whose surface is paved with the material in object, preventively greased with having oil 10 viscosity SAE W 30. During the execution one determines if the material in examination can be suitable for puts down it in specific atmospheres of job. The medium degree of inclination correspondent to the feeling of insecurity of the operator who walks on the plan, defines the classification of the material in one of the five groups that serve like parameter in order to establish the effectiveness degree anti-slippery.

Samples arrived 24/04/2018 (sampling executed by Costumer)

DESCRIPTION TILES : 100x100 cm
TYPE : 1A8 CERCOM TO BE 1061432
TO BE ANTRACITE RET


Test start 26/04/2018
Test finished 26/04/2018

Slide angle : **12,5°**

Classification : **R10**

LEGEND:

<u>Total of the medium values</u>	<u>Group classification</u>
from 6° to 10°	R 9
over 10° until 19°	R 10
over 19° until 27°	R 11
over 27° until 35°	R 12
over 35°	R 13


Laboratory Head
P.I. Riccardo Frabetti