



Geoceramic Researches S.r.l.

Via Bacchello, 9
40050 Monte San Pietro BO - Italy
Tel. 051/6761738 - fax 051/6761736
e-mail : geoceramic@iol.it
home page : <http://digilander.libero.it/GeoceramicRes/>

Laboratory for Experimental and Technological Ceramics and
Brick Industries

TEST REPORT

TS N°: 122/15

DATE 25/05/2015

Spett.le
SERENISSIMA C.I.R.
INDUSTRIE CERAMICHE S.p.A.
Via A. Volta, 9-23/25
42013 CASALGRANDE RE

DIN 51130 : 2014

Determination of anti-slippery characteristic
Work's zone with high risk of slippery
Procedure of test walking – inclined platform.

The test regard work's zone with high risk of slippery; the procedure it previews a slanted plan that it comes covered from the subject participants to the test, whose surface is paved with the material in object, preventively greased with having oil 10 viscosity SAE W 30. During the execution one determines if the material in examination can be suitable for puts down it in specific atmospheres of job. The medium degree of inclination correspondent to the feeling of insecurity of the operator who walks on the plan, defines the classification of the material in one of the five groups that serve like parameter in order to establish the effectiveness degree anti-slippery.

Samples arrived 20/05/2015 (sampling executed by Costumer)

DESCRIPTION TILES : 60x60 cm
TYPE : XTREME WHITE R11 A49

Test start 21/05/2015
Test finished 22/05/2015

Slide angle : **22,0°**

Classification : **R11**

LEGEND:

<u>Total of the medium values</u>	<u>Group classification</u>
from 6° to 10°	R 9
over 10° until 19°	R 10
over 19° until 27°	R 11
over 27° until 35°	R 12
over 35°	R 13

